

3 Northway Lane North Latham,New York 12110. Tollfree:1.800.984.5337 Phone:1.518.956.2980 Fax:1.518.785.4725 *Http://www.marktechopto.com* 

# SPECIFICATION

# *PART NO*. : MT7672F -UY 5.2×4.6mm OVAL LED LAMP








#### Description

### This yellow lamp is made with AlGaInP/GaP chip and yellow diffused

epoxy resin.



Notes:

- 1. All dimensions are in mm.
- 2. Tolerance is  $\pm$  0.25mm unless otherwise noted.

## Description

|             | LED C       |                |                 |
|-------------|-------------|----------------|-----------------|
| Part No.    | Material    | Emitting Color | Lens Color      |
| O V7692F/W[ | AlGaInP/GaP | Yellow         | Yellow diffused |

## Absolute Maximum Ratings at Ta=25

| Parameter                                       | Symbol   | Rating      | Unit                     |
|---|----------|-------------|--------------------------|
| Power Dissipation                               | Pd       | 130         | mW                       |
| Reverse Voltage                                 | Vr       | 5           | V                        |
| D.C. Forward Current                            | If       | 50          | mA                       |
| Reverse (Leakage) Current                       | Ir       | 100         | μA                       |
| Peak Current(1/10Duty Cycle,0.1ms Pulse Width.) | If(Peak) | 200         | mA                       |
| Operating Temperature Range                     | Topr     | -40 to +95  |                          |
| Storage Temperature Range                       | Tstg     | -40 to +100 |                          |
| Soldering Temperature(1.6mm from body)          | Tsol     | 1 0         | For 5 sec.<br>For 3 sec. |

#### **Electrical and Optical Characteristics:**

| Parameter       |            | Symbol | Condition | Min. | Тур. | Max.  | Unit |
|-----------------|------------|--------|-----------|------|------|-------|------|
| Luminous Intens | ity        | Iv     | If=20mA   | 1520 | 2000 |       | mcd  |
| Forward Voltage |            | Vf     | If=20mA   |      | 2.1  | 2.6   | V    |
| Peak Wavelength | l          | λp     | If=20mA   |      | 591  |       | nm   |
| Dominant Wavel  | ength      | λd     | If=20mA   | 584  | 589  | 593   | nm   |
| Reverse (Leakag | e) Current | Ir     | Vr=5V     |      |      | 100   | μA   |
| X7 A 1-         | VERTICAL   | 2 1/2  | If=20mA   |      | 40   |       | 4    |
| ViewingAngle    | HORIZONTAL | 2 1/2  | If=20mA   |      | 70   | ) deg |      |
| Spectrum Line H | alfwidth   | Δλ     | If=20mA   |      | 15   |       | nm   |

Notes:1. The datas tested by IS tester.

2. Customer's special requirements are also welcome.



#### **Specifications for Bin Grading:**

| Iv(mcd) |      |      |
|---------|------|------|
| BIN     | MIN. | MAX. |
| U       | 1520 | 2130 |
| V       | 2130 | 3000 |

#### **Specifications for Vf Group:**

| Vf(V) |      |      |
|-------|------|------|
| Group | MIN. | MAX. |
| V1    | 1.6  | 1.8  |
| V2    | 1.8  | 2.0  |
| V3    | 2.0  | 2.2  |
| V4    | 2.2  | 2.4  |
| V5    | 2.4  | 2.6  |


\*Majority VF bins are highlighted in Yellow.

#### **Specifications for Wavelength Group:**

| d(nm) |      |      |
|-------|------|------|
| Group | MIN. | MAX. |
| X2    | 584  | 587  |
| X3    | 587  | 590  |
| X4    | 590  | 593  |



#### "'O V7692F - WY''''' 5.2×4.6mm OVAL LED LAMP





#### Precautions:

#### TAKE NOTE OF THE FOLLOWING IN USE OF LED

1. Temperature in use

Since the light generated inside the LED needs to be emitted to outside efficiently, a resin with high light transparency is used; therefore, additives to improve the heat resistance or moisture resistance (silica gel, etc) which are used for semiconductor products such as transistors cannot be added to the resin.

Consequently, the heat resistant ability of the resin used for LED is usually low; therefore, please be careful on the following during use.

Avoid applying external force, stress, and excessive vibration to the resins and terminals at high temperature. The glass transition temperature of epoxy resin used for the LED is approximately 120-130 .

At a temperature exceeding this limit, the coefficient of liner expansion of the resin doubles or more compared to that at normal temperature and the resin is softened.

If external force or stress is applied at that time, it may cause a wire rupture.

#### 2. Soldering

Please be careful on the following at soldering.

After soldering, avoided applying external force, stress, and excessive vibration until the products go to cooling process (normal temperature), <Same for products with terminal leads>

(1) Soldering measurements:

Distance between melted solder side to bottom of resin shall be 1.6mm or longer.

(2) Dip soldering :

Pre-heat: 90 max. (Backside of PCB), Within 60 seconds.

Solder bath: 260±5 (Solder temperature), Within 5 seconds.

- (3) Hand soldering: 350 max. (Temperature of soldering iron tip), Within 3 seconds.
- 3. Insertion

Pitch of the LED leads and pitch of mounting holes need to be same.

4. Others

Since the heat resistant ability of the LED resin is low, SMD components are used on the same PCB, please mount the LED after adhesive baking process for SMD components. In case adhesive baking is done after LED lamp insertion due to a production process reason, make sure not to apply external force, stress, and excessive vibration to the LED and follow the conditions below.

Baking temperature: 120 max. Baking time: Within 60 seconds.

If soldering is done sequentially after the adhesive baking, please perform the soldering after cooling down the LED to normal temperature.